

Technical Data Sheet



Product name: CarbonFil™

Date of issue: 29 October 2015

Version: v2

CarbonFil™ is a 20% long stringer carbon fibre reinforced filament – based on our HDglass™ high strength & performance modified PETG (PolyEthylene Terephthalate Glycol-modified) compound – and by that is extremely stiff and yet still very impact resistant.

CarbonFil™ filament is a very easy to print 3D printer filament as it is warp-free, can be printed without a heated bed, has a great thermal stability, an excellent flowing behaviour and a superb first- and interlayer adhesion and does not produce any odours during 3D printing.

Properties	Typical value	Test Method	Test condition
Physical			
Specific gravity	1.19 g/cc	ASTM D792	-
Melt flow rate	-	-	-
Water absorption	-	-	-
Moisture absorption	± 0.13%	-	-
Mechanical			
Impact strength	7.9 KJ/m ²	ASTM D256	Izod Notched @23° C (73° F)
Tensile strength	52.5 Mpa	ISO 527	@Yield 50mm/min (2 inch/min)
Tensile modulus	3800 Mpa	ISO 527	1mm/min
Elongation at break	8%	ISO 527	@ Break 50mm/min (2 inch/min)
Flexural strength	-	-	-
Flexural modulus	± 4600 Mpa	-	-
Hardness	109	ASTM D785	Rockwell R-scale
Thermal			
Print temperature	± 230 - 265° C	-	-
Melting temperature	-	-	-
Viscat softening temp.	± 85° C	ASTM D648	@ 0.455 Mpa (66psi)
Optical			
Haze	-	-	-
Transmittance	-	-	-
Gloss	-	-	-

Product details, certifications and compliance	Diameter	Tolerance	Roundness
HS Code	1.75mm	± 0.05mm	≥ 95%
REACH compliant	2.85mm	± 0.10mm	≥ 95%
RoHS certified			
FDA compliant			

Formfutura VOF	CoC: 55502105	Tel: +31 (0)85 002 0881
Groenestraat 215	VAT: NL851741083B01	Email: info@formfutura.com
6531 HH Nijmegen	EORI: NL851741083	Website: www.formfutura.com
The Netherlands		

All information supplied by or on behalf of Formfutura in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but Formfutura assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the forementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information. Typical values are indicative only and are not to be construed as being binding specifications.